

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
22 February 2001 (22.02.2001)

PCT

(10) International Publication Number  
**WO 01/12769 A1**

- (51) International Patent Classification<sup>7</sup>: C11D 3/37, 7/06, 3/02, C03C 23/00
- (21) International Application Number: PCT/EP00/06361
- (22) International Filing Date: 5 July 2000 (05.07.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 09/372,534 11 August 1999 (11.08.1999) US
- (71) Applicant (for all designated States except AG, AU, BB, CA, CY, GB, GD, GH, GM, IE, IL, IN, KE, LK, LS, MN, MW, NZ, SD, SG, SL, SZ, TT, TZ, UG, ZA, ZW): UNILEVER N.V. [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).
- (71) Applicant (for AG, AU, BB, CA, CY, GB, GD, GH, GM, IE, IL, KE, LK, LS, MN, MW, NZ, SD, SG, SL, SZ, TT, TZ, UG, ZA, ZW only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London, Greater London EC4P 4BQ (GB).
- (71) Applicant (for IN only): HINDUSTAN LEVER LTD [IN/IN]; Hindustan Lever House, 165-166 Backbay Reclamation, 400 020 Mumbai (IN).
- (72) Inventors: ROUILLARD, Carol, Anne; Diverseylever R & D, 3630 E Kemper Road, Sharonville, Cincinnati,
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/12769 A1

(54) Title: ANTI-ETCH AND CLEANING COMPOSITION FOR GLASS BOTTLES

(57) Abstract: A novel anti-etch and cleaning solution is described. The solution comprises a hetero functionalized polymer, caustic and optionally, an anti-etch component and unexpectedly results in glassware that is substantially free of contaminants and etching after washing.

**Anti-Etch and Cleaning Composition  
For Glass Bottles**

**5 Field of the Invention**

This invention is directed to a novel cleaning composition for glassware. More particularly, the invention is directed to an anti-etch and cleaning composition that unexpectedly results in bottles that are substantially free of etching 10 and contaminants after washing.

**Background of the Invention**

Glassware, like domestic dishes and glass bottles used in the soft drink and alcoholic beverage industries, is 15 frequently rewashed, recycled and/or reused. With respect to glass bottles, for example, such a recycling process is extremely advantageous since it reduces the amount of glassware that, for instance, pollutes local neighborhoods and results in non-biodegradable debris in local landfills. 20 Also, the recycling of bottles enables the beverage industry to save money by getting more uses out of the bottles it has invested in.

When recycling glassware, it is imperative that the 25 glassware be washed to the point of being commercially

sterile. Obtaining commercially sterile bottles, for example, from bottles that have been previously used, is not easy since used bottles are often contaminated with dirt, mold, sugar, food coloring, product labels, glue and 5 the like. In order to remove such contaminants from the bottles being cleaned, harsh environments, such as those which employ relatively long contact times, high temperatures, chelators (e.g., ethylene diamine tetraacetic acid [EDTA] and nitrilotriacetic acid [NTA]) and caustic, 10 are used. Such environments typically are successful in "transforming" glassware that was once used into glassware that is substantially free of contaminants and commercially sterile.

15 Unfortunately, however, when bottles are subjected to harsh environments, like those that employ EDTA and NTA, the bottles begin to literally dissolve in the presence of the strong chelators. The dissolution of the glass gives the bottles a scratchy look, making the bottles aesthetically 20 unappealing for consumer use. Moreover, glass dissolution results in free silica in cleaning environments. Free silica often creates problems in equipment used to clean glassware, since free silica often complexes with other

materials and deposits as a silica scale on the equipment used for cleaning the glassware.

Other attempts have been made for cleaning glassware with 5 compositions that do not employ harsh chelating agents like EDTA and NTA. These compositions typically use metal ions (e.g., zinc, beryllium); however, such compositions often do not display superior cleaning capabilities and can pose health, environmental and equipment problems.

10

It is of increasing interest to formulate a composition that results in glassware that is not etched, and contaminant free after washing. This invention, therefore, is directed to a superior anti-etch and cleaning 15 composition that unexpectedly results in glassware, like bottles, that is substantially free of etching and contaminants after washing. Substantially free of contaminants is defined to mean glassware that is about as clean as glassware cleaned with conventional washing 20 solutions, (having strong chelators like EDTA), as analyzed by the Examples which follow.

**Background References**

Efforts have been disclosed for cleaning glassware. In US-A-5,849,095, anti-etch bottle washing solutions are made, and the solutions do not contain a phosphorus comprising 5 polymer.

Other efforts have been disclosed for making cleaning compositions. In US-A-5,622,569, a cleaning composition comprising sodium carbonate, sodium hydroxide and sodium 10 gluconate is described.

Still further, other attempts for making cleaning compositions have been disclosed. In US-A-5,084,198, thixotropic liquid dishwashing detergents that result in 15 improved filming and spotting are described.

**Summary of the Invention**

In a first embodiment, the present invention is directed to an anti-etch and cleaning composition comprising:  
20 a) at least one polymer selected from the group consisting of a hetero functionalized polymer comprising a carboxylic acid group and a hetero functionalized polycarboxylate; and  
b) caustic.

In a second embodiment, the present invention is directed to an anti-etch and cleaning composition comprising:

- a) at least one polymer selected from the group consisting of a hetero functionalized polymer comprising a carboxylic acid group and a hetero functionalized polycarboxylate;
- 5 b) caustic; and
- c) an anti-etch component.

In a third embodiment, the present invention is directed to 10 glassware that has been subjected to the to the anti-etch and cleaning composition described in the first embodiment of this invention.

#### **Detailed Description of the Preferred Embodiments**

15 There generally is no limitation with respect to the type of hetero functionalized polymer comprising a carboxylic acid group that may be used in this invention other than that the polymer results in an anti-etch and cleaning composition that renders dirty glassware substantially free 20 of etching and contaminants after washing. Such polymers typically comprise backbones that are derived from polypeptides, polyolefins, polyesters and polyethers, including homopolymers and copolymers (including terpolymers) prepared therefrom. The polymers also

comprise carboxylic acid groups that are, for example, substituted on to the precursor monomeric units used to make each polymer.

5 There generally is no limitation with respect to the hetero functionalized polycarboxylate polymer used in this invention, other than that the polymer results in an anti-etch and cleaning composition that renders dirty glassware substantially free of etching and contaminants after  
10 washing. The preferred polycarboxylate polymers include those having hetero groups as grafts, terminating groups or both. The most preferred polycarboxylate polymers used in this invention are phosphino carboxylic acids and phosphono carboxylic acids having sulfonate groups, both of  
15 which are commercially available from FMC Corporation and sold under the names of Belclene 750 and Belclene 745, respectively. Other most preferred hetero functionalized polycarboxylate polymers which may be used in this invention include polymers having a portion derived from  
20 diacids. The most preferred diacid derived hetero functionalized polycarboxylate polymer used in this invention is one derived from the copolymerization of maleic acid, an alkyl acrylate (such as a C1-C4 alkyl acrylate) and a vinyl acetate. Such a terpolymer is

commercially available from FMC Corporation and sold under the name of Belclene 730.

There generally is no limitation with respect to the 5 hetero groups used to functionalize the polymers which may be used in this invention other than that the hetero groups enhance the solubility, chelating effect or both of the polymer. The preferred hetero groups are those comprising elements having a valence number of 5 or 6, with phosphino, 10 phosphono and sulfonate groups being the most preferred hetero groups.

As to the hetero groups employed in this invention, such groups typically make up from about 0.1% to about 5.0%, and 15 preferably, from about 0.15% to about 3.0%, and most preferably, from about 0.5% to about 1.5% by weight of the total weight of the hetero functionalized polymer comprising a carboxylic acid group or the hetero functionalized polycarboxylate, including all ranges 20 subsumed herein. The primary factor with respect to determining the molecular weight of the hetero functionalized polymer used in this invention is the ability of the polymer to result in an anti-etch and cleaning composition able to achieve the desired results of

this invention. Generally, however, the polymers have a weight average molecular weight ranging from about 500 to about 125,000.

5 When formulating the anti-etch and cleaning composition of this invention, there is no limitation with respect to the amount of hetero functionalized polymer used other than that the amount used results in a composition capable of achieving the desired results of this invention.

10 Typically, the anti-etch and cleaning composition of this invention will have enough hetero functionalized polymer to produce an in use solution comprising from about 5 to about 5000, and preferably, from about 25 to about 3000, and most preferably, from about 250 to about 1200 ppm hetero  
15 functionalized polymer. As used herein, in use solution is defined to mean the overall cleaning solution used in a conventional bottle cleaning system.

As to the caustic employed in this invention, there is no  
20 limitation with respect to the caustic employed as long as the caustic selected is one which results in an anti-etch and cleaning composition capable of achieving the desired results of this invention. Typically, however, the caustic employed is a Group IA or IIA hydroxide, ammonium

hydroxide, or a mixture thereof. The preferred caustic is a hydroxide of sodium or potassium, with sodium hydroxide being the most preferred.

5 The amount of caustic employed is limited only to the extent that an anti-etch and cleaning composition may be formulated. Typically, the amount of caustic used is enough to result in an in use solution comprising from about 0.25% to about 20.0%, and preferably, from about 0.5% 10 to about 15.0%, and most preferably, from about 1.0% to about 7.5% by weight caustic.

Regarding the anti-etch component used in the anti-etch and cleaning composition of this invention, such a component is 15 preferred but optional and limited only to the extent that it may be used to prepare the desired composition of this invention. Typically, however, the anti-etch component employed in this invention is one comprising at least one carboxylic acid group. The preferred anti-etch component 20 used in this invention is a polycarboxylic acid, (without a hetero group), and the most preferred anti-etch component is a polyacrylate, like a Group IA or IIA polyacrylate, with a sodium polyacrylate (e.g., Alcosperse 408, weight average molecular weight of about 3000, an anionic

terpolymer made commercially available by Alco) being especially preferred.

The amount of anti-etch component employed in the anti-etch 5 and cleaning composition of this invention is typically enough to result in an in use solution comprising from about 1.0 to about 1000, and preferably, from about 20.0 to about 500.0 and most preferably, from about 50.0 to about 150 ppm of the anti-etch component.

10

It is also within the scope of this invention to use conventional additives in the anti-etch and cleaning composition. Such additives include crystal growth inhibitors, like Acusol 505N or Acusol 479N, copolymers 15 made commercially available from Rohm & Haas. Other additives include buffers, like sodium bicarbonate, sodium carbonate, sodium phosphate, sodium disilicate and mixtures thereof. Still further, other additives which may be employed in this invention include phosphonates (acids and 20 salts) such as aminotri (methylene-phosphonic acid) and aminotri (methylene-phosphonic acid), pentasodium salt, both of which are sold under the name of DEQUEST 2000 and DEQUEST 2006, respectively and made commercially available by Solutia.

The amount of phosphonate that may be employed in the invention is often enough to produce an in use solution comprising from about 1 to about 2000, and preferably, from 5 about 5 to about 1500, and most preferably, from about 50 to about 1100 ppm phosphonate.

Agents like gluconic acid and water soluble salts thereof may also be used in this invention to enhance the chelating 10 action of the composition of this invention. Other agents that enhance the chelating action of the composition of this invention include an alkali metal glucoheptonate, alkali metal boroheptonate and mixtures thereof. Such agents that enhance chelating action typically result in an 15 in use solution having from about 200 to about 2000 ppm chelating agent.

Still other additives which may be used in the anti-etch and cleaning composition of this invention include 20 surfactants (e.g., anionic, nonionic and/or amphoteric). The nonionics may generally be classified as polyalkylglycosides. A preferred polyalkylglycoside is Glucopon 425CS, which is commercially available from Henkel Care Chemicals. Examples of other surfactants which may be

used in this invention include sodium salts of carboxylated linear alcoholalkoxylates, lauryl sulfate, sodium xylene sulfonate, toluene sulfonic acid and salts thereof, sulfosuccinate salts, fatty acids and their salts, anionic 5 glucoesters such as disodium cocoglucoside citrate, disodium cocoglucoside sulfosuccinate and sodium cocopolyglucose tartrate, iminodipropionates such as disodium tallow iminodipropionate, as well as disodium cocamphodiacetate and cocoamphocarboxylacinate, as well as 10 disodium cocoamphodiacetate and cocoamphocarboxylacinate, and the imidazolines. It should be further noted that water may be added as the balance to the anti-etch and cleaning composition of this invention, if desired. A more detailed description of the additives which may be used in 15 this invention may be found in United States Patent 5,849,095, the disclosure of which is incorporated herein by reference.

As to the glassware which is subjected to the anti-etch and 20 cleaning composition of this invention, such glassware is not limited and includes bottles from the soft drink and alcoholic beverage industries. Subjected to, as used herein, is defined to mean glassware that has been cleaned with the anti-etch and cleaning composition of this

invention, whereby the cleaning takes place in conventional bottle washers.

The examples that follow are provided to illustrate and facilitate an understanding of the present invention. The examples are not intended to restrict the scope of this invention.

**Example 1**

10 Standard soft drink bottle soil was made according to the guidelines set forth by the Society of Soft Drink Technologists. The soil was made, in the form of a slurry, by charging a mixing vessel with the following components:

- 15 - 150 grams Redart red clay, 100 mesh or finer (Cedar Heights Clay Company, Oak Hill, OH)
- 22.5 grams Durham Water Putty (Aanold Durham Co., Des Moines, IA)
- 6.0 grams Xantham Gum
- 20 - 4.5 grams Malt Extract (Difco Laboratories Inc., Detroit, MI)
- 4.5 grams Yeast Extract (Difco Laboratories Inc., Detroit MI)
- 7.5 grams Peptone (Difco Laboratories Inc., Detroit

MI)

- 15.0 grams Dextrose (Difco Laboratories Inc., Detroit MI)
- 1500 ML deionized water.

5

The components were mixed, and the resulting homogeneous slurry was used as the soft drink bottle soil in the examples which follow.

10 **Example 2-6**

Six 1L volumetric flasks were each charged with 60 grams of aqueous sodium hydroxide (50% NaOH), 5 grams sodium carbonate and 1000mL of deionized water. The flasks were also charged as follows:

15

<u>Flask No.</u>	<u>Additional Components</u>
1	No additional components
2	0.5g sodium tripolyphosphate
3	2.0g of commercially available
20	bottle cleaning composition*
4	1.0g Belclene 745 (0.5g active) + 0.1g Alcosperse 408
5	1.0g Belclene 750 (0.5g active) + 0.1g Alcosperse 408

\* Conventional and commercially available bottle cleaning composition, comprising about 80% raw EDTA (about 39% active) and about 5.0% sodium gluconate (percents by weight).

5

**Example 7-11**

Five groups of six about 1" x 3" washed glass slides were weighed. Exactly 1.0 gram of the soil produced in Example 1 was applied to one side of each glass slide. The soil 10 was uniformly applied with a policeman to about a two inch portion of each glass slide. The soiled slides (soil up) were placed on a rack (under hood) and allowed to dry overnight at room temperature. After about 12 hours of drying at room temperature, the slides were dried in an 15 oven set at about 70°C for about 3 hours. The resulting five sets of slides were prepared to mimic used/dirty bottles found in many beverage industries.

**Example 12**

20 The five solutions prepared in Examples 2 thru 6 (corresponding to flask Nos. 1-5) were each transferred independently, to a stainless steel can of a commercially available Terg-o-tometer (commercially available from United States Testing Co., Inc.). The

solutions were heated to about 70°C. The glass slides prepared in Examples 7-11 were clipped to rings (6 slides per ring with soil facing inward). Each ring was lowered into a stainless steel can of the Terg-o-tometer, whereby 5 each can had one of the solutions prepared in Examples 2-6.

The rings were lowered into each can to the point where the soiled portion of each slide was completely submerged in solution. Once submerged in the solutions, each set of slides was subjected to agitation (about 25 rpm for about 5 10 minutes and 40 rpm for 25 minutes). At the end of the 30 minute period, the rings and slides were removed and the slides were rinsed (dipped) into deionized water. The washed slides were removed from the rings and each group of six slides was oven dried for about 1 hour at about 50°C. 15 The slides were removed from the oven and allowed to cool.

Each set of six slides was again weighed. The weight of the slide sets, after being subjected to solution and deionized water, was subtracted from the original weight of the slide set plus the dried soil. The weight difference 20 calculated is set forth in Table 1 below. Each weight difference corresponds to the percent soil removed.

**Table 1**

<u>Solution No.</u>	<u>(from corresponding flasks)</u>	<u>Percent</u>
		<u>Soil removal</u>
1		39
5	2	37
	3	58
	4	56
	5	58

**10 Example 13**

Five sets of three slides, identical to those used in the Examples above, except that the slides were not soiled, were weighed. Each set of glass slides was placed in a sealed, stainless steel vessel charged with one of the 15 solutions described in Examples 2 thru 6. The glass slides were submerged in the solutions (maintained at about 70°C) for about 72 hours. After the 72 hour period, the slides were hand washed with a commercially available dishwashing detergent, rinsed with deionized water, submerged in an acidic bath (7.5% phosphoric acid) for about 20 minutes, rinsed again with deionized water, dried and, again, weighed. The data in Table II, represents the weight difference of each set of slides. The weight difference was calculated by subtracting the weight of each set after

being submerged in the solutions from the original weight of the set. The weight difference depicts how much the slides etched (how much silica dissolution) in each solution whereby the weight difference is depicted as 5 percent etching.

Table II

Solution (from corresponding flasks)	Percent Etching
1	1.37
10	0.85
3	2.32
4	0.02
5	0.03

15 What maybe understood from the data above, the superior anti-etching and cleaning solution of this invention (e.g., solutions 5 and 6) unexpectedly result in glass that is, simultaneously, free of contaminants and etching after washing. Furthermore, the unexpected results obtained in  
20 this invention are achieved without requiring strong chelators, like EDTA and NTA, in the composition.

**Claims**

1. An anti-etch and cleaning composition comprising:
  - a) at least one polymer selected from the group consisting of a hetero functionalized polymer comprising a carboxylic acid group and a hetero functionalized polycarboxylate; and
  - b) caustic.
2. The anti-etch and cleaning composition according to claim 1 wherein the hetero functionalized polymer comprising a carboxylic acid group is a polymer comprising a polypeptide, polyolefin, polyester or polyether backbone.
3. The anti-etch and cleaning composition according to claim 1 wherein the hetero functionalized polycarboxylate is derived from a diacid.
4. The anti-etch and cleaning composition according to claim 1 wherein the hetero functionalized polycarboxylate is derived from maleic acid, a C<sub>1-4</sub> alkyl acrylate and vinyl acetate.

5. The anti-etch and cleaning composition according to claim 1 wherein the hetero group is a group comprising an element having a valence number of 5 or 6.
6. The anti-etch and cleaning composition according to claim 5 wherein the hetero group is a phosphino, phosphono or sulfonate group.
7. The anti-etch and cleaning composition according to claim 1 wherein the hetero functionalized polycarboxylate comprises a phosphono and sulfonate group.
8. The anti-etch and cleaning composition according to claim 1 wherein the hetero functionalized polymer comprising a carboxylic acid group and the hetero functionalized polycarboxylate comprise from about 0.1% to about 5.0% by weight hetero group.
9. The anti-etch and cleaning composition according to claim 1 wherein the amount of hetero functionalized polymer in the anti-etch and cleaning solution is enough to generate an in use solution

comprising from about 5 to about 5000 ppm of hetero functionalized polymer.

10. The anti-etch and cleaning composition according to claim 1 wherein the caustic comprised at least one member selected from the group consisting of a Group IA or IIA hydroxide and ammonium hydroxide.
11. The anti-etch and cleaning composition according to claim 10 wherein the caustic is a Group IA hydroxide, and the Group IA hydroxide is sodium hydroxide.
12. The anti-etch and cleaning composition according to claim 1 wherein the composition further comprises an anti-etching component.
13. The anti-etch and cleaning composition according to claim 12 wherein the anti-etching component comprises a carboxylic acid group.
14. The anti-etch and cleaning composition according to claim 13 wherein the anti-etching component comprising a carboxylic acid group is a group IA or IIA polyacrylate.

15. Glassware having been contacted with an anti-etch and cleaning composition comprising:

- a) at least one polymer selected from the group consisting of a hetero functionalized polymer comprising a carboxylic acid group and a hetero functionalized polycarboxylate; and
- b) caustic.

16. The glassware according to claim 15 wherein the glassware is a soft drink or alcoholic beverage bottle.

17. The glassware according to claim 15 wherein the anti-etch and cleaning composition further comprises an anti-etching component.

# INTERNATIONAL SEARCH REPORT

Internat...al Application No

PCT/EP 00/06361

A. CLASSIFICATION OF SUBJECT MATTER	IPC 7 C11D3/37	C11D7/06	C11D3/02	C03C23/00
-------------------------------------	----------------	----------	----------	-----------

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C11D C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 774 506 A (ROHM & HAAS) 21 May 1997 (1997-05-21) page 5, line 14 - line 54; claims ---	1-4,9-17
A	WO 97 38079 A (UNILEVER PLC ;UNILEVER NV (NL)) 16 October 1997 (1997-10-16) cited in the application the whole document ---	1,9-13
X	---	15-17
A	WO 96 16159 A (UNILEVER NV ;UNILEVER PLC (GB)) 30 May 1996 (1996-05-30) claims ---	1,9-17
A	GB 965 215 A (UNILEVER) 29 July 1964 (1964-07-29) claims ---	1,9-17
	-/-	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

2 November 2000

Date of mailing of the international search report

09/11/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Grittern, A

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP 00/06361

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 11, 29 November 1996 (1996-11-29) & JP 08 176589 A (LION CORP), 9 July 1996 (1996-07-09) abstract -----	1,9-15, 17

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

Interr	nal Application No
PCT/EP 00/06361	

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP 0774506	A 21-05-1997	BR 9605621 A CA 2190235 A CN 1158889 A JP 9194882 A US 5770555 A		18-08-1998 21-05-1997 10-09-1997 29-07-1997 23-06-1998
WO 9738079	A 16-10-1997	AU 2029397 A BR 9708539 A CA 2251708 A EP 0892848 A JP 11514021 T US 6106633 A US 5849095 A ZA 9702976 A		29-10-1997 03-08-1999 16-10-1997 27-01-1999 30-11-1999 22-08-2000 15-12-1998 08-10-1998
WO 9616159	A 30-05-1996	AU 4173596 A BR 9509693 A DE 69516537 D DE 69516537 T EP 0793711 A ES 2145937 T FI 972124 A		17-06-1996 14-10-1997 31-05-2000 10-08-2000 10-09-1997 16-07-2000 19-05-1997
GB 965215	A	CA 666119 A		
JP 08176589	A 09-07-1996	NONE		